

FABRIC SPECIFICATION SHEET

WM12K

Style		WM12K
Construction		Multi-filament plain weave
Weight	g/m ²	460 ± 10%
Thread Count	Per 25mm	17 x 16
Air Permeability		Impermeable
Fibre		Kevlar (Aramid)
Average Tensile Strength		<u>Fabric</u> Warp 640 kg Weft 725 kg <u>Single Yarn</u> Warp 62kg Weft 63 kg
Finish		Scoured and heat set
Max. Operating Temperature	°C	260 300—Surge
Description		Woven Kevlar Aramid



1620 Lake Drive West
 Chanhassen, MN 55317
 Tel: 877-236-3539 Fax: 952-279-5205
 E-mail: Sales@powder-solutions.com
 www.powder-solutions.com

